

## EOS CobaltChrome MP1 for EOS M 100



# EOS CobaltChrome MP1 EOS M 100 | 30 μm

EOS CoCr MP1 conforms to chemical composition UNS R31538. Parts built can be machined, welded, polished and coated as required. They are suitable for a wide variety of applications.



# Main Characteristics

- High carbon CoCrMo based superalloy
- $\longrightarrow$  Good corrosion and wear resistance
- → Good mechanical properties

**Product Information** 

Current TRL

DMLS System

Material

Process

Typical part properties

As manufacturted

As manufactured

vertical

horizontal

### Typical Applications



#### Layer thickness 30 µm

Tensile strength

Rm [MPa]

1200

1340

Jewelry

Volume rate 1.5 mm³/s Porosity <0,2 %

Elongation at break

A [%]

13

11

Headquarters

EOS GmbH Electro Optical Systems Robert-Stirling-Ring 1 D-82152 Krailling/Munich Germany Phone +49 89 893 36-0 info@eos.info

www.eos.info in EOS ¥ EOSGmbH ③ EOS.global ■ EOSGmbH #ShapingFuture #ResponsibleManufacturing

Further Offices

EOS France Phone +33 437 497 676

EOS Greater China Phone +86 21 602 307 00

EOS India Phone +91 443 964 8000

EOS Italy Phone +39 023 340 1659

EOS Japan Phone +81 45 670 0250

EOS Korea Phone +82 2 6330 5800

EOS Nordic & Baltic Phone +46 31 760 4640

EOS North America Phone +1 877 388 7916

EOS Singapore Phone +65 6430 0463

EOS UK Phone +44 1926 675 110



#### Status 01/2022

EOS is certified according to ISO 9001. EOS® and DMLS® are registered trademarks of EOS GmbH Electrical Optical Systems in some countries. For more information visit www.eos.info/trademarks.

3

EOS M 100

EOS CobaltChrome MP1

CoCr\_030\_100 M100

Yield strength

Rp<sub>0.2</sub> [MPa]

830

1040

Important Note

This data sheet specifies the powder properties of the EOS powder type referenced above. If you purchase powder from EOS, EOS will deliver such powder in conformity with the version of this data sheet prevailing at the time of your order. If you purchase powder from any source other than EOS, EOS makes no warranties or representations with respect to powder properties to you whatsoever, and claims with respect to the quality or properties of EOS powder are available only against the seller of such powder in accordance with your agreement with the seller, not against EOS. EOS data sheets are subject to change without notice. This data sheet does not constitute a guaranty or warranty of properties or fitness for a specific purpose and may not be relied upon as such.

Part properties stated above are provided for information purposes only and EOS makes no representation or warranty whatsoever, and disclaims any liability, with respect to actual part properties achieved with this material. Part properties are subject to variation and dependent on factors such as system parameters, process and test geometries. Therefore actual part properties may deviate and users of this material are exclusively responsible to determine its suitability for the intended use. The part properties stated above have been determined by testing this material with above specified type of EOS Laser Powder Bed Fusion system, EOSYSTEM and EOSPRINT software version, parameter set and operation in compliance with parameter sheet and operating instructions. Part properties are measured with specified measurement methods using defined test geometries and procedures. Further details of the test procedures used by EOS are available on request.